



Acrylic Crack Filler Product Specifications

Description and Usage

Latex-ite® Acrylic Crack Filler is 100% acrylic latex fortified with mineral fillers and synthetic fibers. It is highly elastomeric, combining superb bonding capacity with exceptional flexibility and resiliency. Latex-ite® Acrylic Crack Filler is designed to be "trowel applied". Latex-ite® Acrylic Crack Filler is used for small cracks (1/8-1/4") and minor surface irregularities. The surface upon which Latex-ite® Acrylic Crack Filler is to be applied must be free of dirt, loose or flaking paint, oily materials or chemical residues, vegetation of any sort and any other debris or foreign matter that may prevent the proper product adhesion.

Coverage

CRACK: One (1) gallon of Latex-ite® Acrylic Crack Filler will approximately cover 8-10 linear feet of crack measuring 1/4' wide to 1' deep.

Drying Time

Latex-ite® Acrylic Crack Filler must be allowed to thoroughly dry between coats. Complete projects should be allowed 24 hours drying time before releasing to play.

Mix Design

Latex-ite® Acrylic Crack Filler is ready-to-use/ do not dilute.

Application

Apply Latex-ite® Acrylic Crack Filler using a trowel or spatula. Coverage will vary depending on the width and depth of the crack.

Features and Benefits

- Remains Flexible
- 100% Acrylic
- Eco Friendly
- Ready to Use

Limitations and Precautions

- Latex-ite® Acrylic Crack Filler should not be applied when ambient temperature is below 50° F or when surface temperature is above 140° F.
- Do not apply when rain is imminent.
- Do not store in direct sunlight. Keep from freezing.
- New asphalt should cure for at least 14 days; concrete shall cure for 28 days.
- Latex-ite® Acrylic Crack Filler will not prevent structural cracking from reoccurring.